



TECHNICAL DATA SHEET

URETAHNE 321

RESTRICTIONS

Restrict the use of the floor to light traffic, non-harsh chemicals and water until the coating is fully cured. Depending on actual complete system application, surface may be slippery, especially when wet or contaminated; keep surface clean and dry.

MIXING

For best results use a high quality 3/8" nap roller. Material has to be applied a minimum of 500 sq. ft. per gallon uniformly for proper appearance and development of physical properties. The epoxy basecoat must be abraded/deglossed for proper adhesion. All new concrete must be cured for at least 30 days. Color or gloss may be affected by humidity, temperatures, chemical exposure, application thickness, exposure to lighting such as sodium vapor lights. Slab on grade requires moisture barrier. Colors may vary from batch to batch, therefore, use only product from the same batches for an entire job. Do not use if relative humidity is below 50%. Substrate temperature must be 5°F above dew point. Tire contact may cause staining and discoloration. Physical properties are typical values and not specifications.

PACKAGING

1 GALLON KITS

PART A	1 QRT
PART B	96 OZ
PART C	0.5 LBS

WARNING! SLIP AND FALL PRECAUTIONS

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slipresistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. omega custom coating recommends the use of angular slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. omega custom coating will not be responsible for injury incurred in a slip and fall accident.

Handling Precautions

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin. Some individuals may be allergic to epoxy resin. Protective gloves and clothing are recommended.

WARRANTY

omega custom coatings products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification.



MADE IN USA