



TECHNICAL DATA SHEET

RAPID MENDER

MIXING

1 to 1 mix ratio. In measuring cup pour out equal parts of A & B and slowly drill stir while adding 2 parts Silica Sand for body and added strength. i.e. -2 ounces of A, mixed with 2 ounces of B for a total of 4 liquid ounces, you will now add 8 ounces of silica sand and thoroughly drill stir for 30-45 seconds...POUR IMMEDIATELY...mix only what you can use in 3-5 minutes. - For a lower - more pourable viscosity, less aggregate may be added.

NOTE: 30 grit silica sand is the standard size generally added but you can choose to use a smaller grit such as 60 or 90 for an even finer and smoother finish.

LIMITATIONS

Rapid Mender™ is designed for use on interior or exterior concrete surfaces. It is intended for dormant cracks, dormant contraction joints, spall repair and more. Rapid Mender™ is designed to restore the concrete back to original design parameters. Underlying causes of cracking or deterioration should be addressed before making repairs. It must be applied to concrete free of surface moisture, dirt or contaminants.

LIMITATIONS

Concrete must be clean, dry and free of dirt and contaminants. Use mechanical methods to remove loose concrete and profile hard trowled surfaces. Use surface applied heat to remove ice or frost if present.

PACKAGING

3 GALLON KITS

PART A	2 GAL
PART B	1 GAL

3 GALLON KITS

PART A	2 GAL
PART B	1 GAL

WARNING! SLIP AND FALL PRECAUTIONS

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slipresistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. omega custom coating recommends the use of angular slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. omega custom coating will not be responsible for injury incurred in a slip and fall accident.

Handling Precautions

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin. Some individuals may be allergic to epoxy resin. Protective gloves and clothing are recommended.

WARRANTY

omega custom coating products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification.



MADE IN USA